








**EQUIVALENCIAS INTERNACIONALES DE LAS ALEACIONES DE ALUMINIO**

USA	ESPAÑA	FRANCIA	ALEMANIA	GB	CANADA	ITALIA
						
1050/1145	L-3051	A 5	AL 99,5	2L 48	1 S	4507
1070	L-3071	A 7	AL 99,7	2L 48	-	4508
1100/1200	L-3001	A 4	AL 99	1 C	2 S	3567
2011	L-3192	AU5 PbBi	AlCuBiPb	FC 1	M28S	6362
2017	L-3120	AU 4G	AlCuMg1	H 14	17 S	3579
2030	L-3121	AU 4Pb	AlCuMgPb	-	-	-
5083	L-3321	AG4,5 MC	AlMg4,5Mn	N 8	D54S	7790
5086	L-3322	AG4 MC	AlMg4Mn	-	E54S	5462
5754	L-3390	AG3 M	AlMg3	-	53 S	3059
6060/6063	L-3441	AGS	AlMgSi0,5	H 9	50 S	3569
6082	L-3453	ASG M0,7	AlMgSi1	H 30	-	3571
7022	L-3741	AZ 5G	AlZn4,5Mg1	H 17		7791
7075	L-3710	AZ5 GU	AlZnMgCu	L 160	75 S	3735